

DESCRIPTION

Deacon 8875 is a thick, fibrous, thermal reactive paste sealing/refractory hybrid used in high temperature and high-pressure applications. In the presence of heat, Deacon 8875 will form a mechanical (“mechanical type”) seal. Deacon 8875 will not cement the flanges together, thus, it will not interfere with future repairs of metal-to-metal joints. Deacon 8875 is unaffected by thermal cycling.

TEMPERATURE RANGE

500°F to 1800°F.

RECOMMENDED APPLICATIONS

Deacon 8875 can be used as gasket dressing to improve the sealing capability of many gaskets. Deacon 8875 can also be applied to many types of gaskets (including spiral wound) to reseal them, thereby prolonging their useful life. Deacon 8875 can be used as the only sealant on low-tolerance metal-to-metal joints.

Deacon 8875 is troweled onto the sealing surface in a complete, uniform, thin coating. Note: Deacon 8875 will flow filling small voids, and surface irregularities creating a seal between the gasket and the flange surface where the most leak problems originate. Deacon 8875 can also be used as a standalone compound on metal-to-metal flanges that are warped, cut, or pitted.

TYPICAL APPLICATION

Turbine Slip Casing, Any Metal to Metal Joints, Pump Casing, Leaking Gaskets, Boilers, Doors, Steam Traps, Ductwork, Stacks, Flanges, Heat Exchangers, Gaskets Dressing, Exhaust Systems.

FEATURES

Ease of application. Achieves seal before full cure. Fast, easy repairs. High-pressure tolerance, high temperature tolerance, and high chemical tolerance. Hot Air, Solvents, Oils, Steam, Liquors, Hydrocarbons, Corrosive Conditions. Creates a mechanical seal. High wear resistance. Unaffected by thermal cycling. Applications as a gasket dressing. Deacon 8875 improves the sealing capability of many gaskets' materials.

PACKAGING

Quart, Gallon, 5 Gallon Pail

SHELF LIFE

Two years in unopened containers.

INSTRUCTIONS

1. Surface should be clean and dry (free from oil or foreign material to ensure proper sealing/adhesion)
2. Apply a thin coat to sealing surface with a putty knife
3. Close and tighten joint (torqued to the equipment manufacturer's specifications if sealing a bolted flange)
4. Product will cure in service with heat (**See Note**)

NOTE

In high pressure applications or when pressure testing at ambient, it is recommended to pre-cure with a heat gun, oven, or dry fire/blow down at atmospheric (running heat without pressure). Unlike silicone or epoxy products, our thermosetting sealants require heat to cure.

CURING

The chart below is a general guideline for the time required for a full cure at various temperatures. A seal will be achieved before a full cure is reached.

300°F	2 hrs
400°F	1 hr
500°F +	<1 hr

FOR INDUSTRIAL USE BY PROFESSIONALLY TRAINED PERSONNEL ONLY.

CONSULT SDS & TECH SHEET FOR ALL SAFETY, TECHNICAL, & WARRANTY INFORMATION BEFORE USE. **NOT RECOMMENDED FOR USE ON NUCLEAR APPLICATIONS**

LIMITED WARRANTY

For warranty information please visit http://www.jetlube.com/pdf/Limited_Warranty_At_Delivery_Deacon.pdf You can also email us at sales@jetlube.com